

# PERLENTOP

## glossy

### LWC Offset (glossy)

Perlentop is produced on base of high quality wood chips, recycled household papers and cellulose.

### Technical Parameters

	Testing method	Dimension	Target					
<b>Grammage</b>	ISO 536	g/m <sup>2</sup>	<b>51</b>	<b>54</b>	<b>57</b>	<b>60</b>	<b>65</b>	<b>70</b>
Brightness	ISO 2470/2471	%	73.0	73.0	75.0	76.0	76.0	76.0
Printing Opacity	ISO 2470/2471	%	91	91	91	92	93	94
Gloss	Tappi T 480 Lehmann 75°	%	41	43	45	45	45	45
Spez. Volume	ISO 534-88	cm <sup>3</sup> /g	1.0	1.0	0.9	0.9	0.9	0.9
Colour Value a	ISO 2470/2471		-0.05	-0.05	-0.05	-0.05	-0.05	-0.05
Colour value b	ISO 2470/2471		0.7	0.7	0.7	0.7	0.7	0.7

#### Finishing

Reel width  
Reel diameter  
Core diameter

#### Reeldimensions

min.	max.
39 cm	200 cm
100 cm	125 cm
7.6 cm	

#### Tolerances

min.	max.
- 1 mm	+ 1 mm
- 5 cm	+ 1 cm

Perlen Papier AG reserves the right to adjust the standard substances, the hue and other qualities of the product in conformity with the developments in the market and the latest research.

Our products are available as well as with FSC certificate.

Perlen, 01/01/2010

**Perlen Papier AG, Perlenring 1, CH-6035 Perlen, phone +41 41 455 80 00, fax +41 41 455 80 01**  
**[info@perlen.ch](mailto:info@perlen.ch)**

[www.perlen.ch](http://www.perlen.ch)