

PERLENTOP

satin

QUALITY

LWC Offset (satin)

Perlentop is produced on base of high quality wood chips, recycled household papers and cellulose.

Technical Parameters

	Testing method	Dimension	Target				
Grammage	ISO 536	g/m ²	54	57	60	65	70
Brightness	ISO 2470/2471	%	78.0	79.0	82.0	82.0	82.0
Printing Opacity	ISO 2470/2471	%	91	92	94	94.5	95.5
Gloss	Tappi T 480 Lehmann 75°	%	20	20	20	20	20
Spez. Volume	ISO 534-88	cm ³ /g	1.0	1.0	1.0	1.0	1.0
Colour value a	ISO 2470/2471		0.9	0.9	0.9	0.9	0.9
Colour value b	ISO 2470/2471		-2.2	-2.2	-2.2	-2.2	-2.2

Finishing

	Reeldimensions		Tolerances	
	min.	max.	min.	max.
Reel width	39 cm	200 cm	- 1 mm	+ 1 mm
Reel diameter	100 cm	120 cm	- 5 cm	+ 1 cm
Core diameter	7.6 cm			

Perlen Papier AG reserves the right to adjust the standard substances, the hue and other qualities of the product in conformity with the developments in the market and the latest research.

Our products are available as well as with FSC certificate.

Perlen, 01/02/2011

Perlen Papier AG, Perlenring 1, CH-6035 Perlen, phone +41 41 455 80 00, fax +41 41 455 80 01
info@perlen.ch
www.perlen.ch