

Standard Newsprint

Perlenpress is produced from high quality wood chips and recycled household papers.

Technical Parameters

	Method	Dimension	Target Value		
Substance	ISO 536	g/m ²	42	45	48.8
Brightness	ISO 2470/2471	%	59	59	59
Opacity	ISO 2470/2471	%	92	93	94
Bulk*	ISO 534	cm ³ /g	1.25 - 1.35	1.25 - 1.35	1.25 - 1.35
Smoothness	ISO 8791/PPS 2.0	µm	2.2	2.2	2.2
Colour Value a	ISO 2470/2471 (D65/10°)	-	-0.3	-0.3	-0.3
Colour Value b	ISO 2470/2471 (D65/10°)	-	2.5	2.5	2.5

*value is subject to fluctuations in production

Finishing

Reel width
Reel diameter
Core diameter

Reel dimensions

min.	max.
35 cm	300 cm
100 cm	150 cm
76 mm or 150 mm	

Tolerances

min.	max.
- 1 mm	+ 1 mm
- 5 cm	+ 1 cm

Please contact our Sales team for reel widths smaller than 60 cm

Perlen Papier AG reserves the right to adjust the target values according to research and market developments. Technical tolerances are in line with industry standards.

All qualities are available with the following environmental labels on request:



Perlen, January 2021

Perlen Papier AG, Perlenring 1, CH-6035 Perlen, Switzerland
+41 41 455 80 00
info@perlen.ch

www.perlen.ch